



# Scotchmate™ Reclosable Fasteners

## SJ3586FR and SJ3587FR

### Polyester Flame Resistant Hook and Loop

**Product Description**

3M™ Scotchmate™ Reclosable Fasteners offer advanced closure alternatives to zippers, screws, snaps, hooks, bolts and more. They offer greater design flexibility, faster product assembly, smoother and cleaner exterior surfaces and improved product performance in many applications. The hook and loop fasteners consist of two strips of polyester fabric which engage to form a quick fastening attachment. Simply pull the strips apart by hand to disengage.

The woven hook is covered with tiny, stiff hooks, about 300 hooks per square inch (46/sq. cm.). The woven loop is covered with thousands of soft, pliable napped loops, providing for thousands of openings and closings (cycles). The hook and loop are preshrunk to insure maximum dimensional stability and flatness.

These hook and loop fasteners are coated on the backside with a unique fire resistant rubber based pressure sensitive adhesive formulated to meet the requirements of the EU Directive 2003/44/EC amending the Council Directive 76/769/EEC, [http://europa.eu.int/eur-lex/pri/en/oj/dat/2003/1\\_042/1\\_04220030215en00450046.pdf](http://europa.eu.int/eur-lex/pri/en/oj/dat/2003/1_042/1_04220030215en00450046.pdf) concerning chemical usage in products. Scotchmate reclosable fasteners also provide flame resistance when tested per FAR 25.853 and other common flammability tests. This adhesive functions over a range of temperatures and humidity permitting these fasteners to be easily and conveniently attached to a variety of substrates.

**Product Construction**

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

	<b>3M™ Scotchmate Reclosable Fastener SJ3586FR (Hook)</b>	<b>3M™ Scotchmate Reclosable Fastener SJ3587FR (Loop)</b>
<b>Material of Construction</b>	Hook or Loop Backing Adhesive Adhesive Color	Polyester Polyester Flame Resistant Synthetic Rubber Translucent White
<b>Standard Colors<sup>(a)</sup></b>	Black, White, Beige	
<b>Thickness<sup>(b)</sup></b>	Inches (mm)	
	maximum unmated	3/32" (2.4 mm)      4/32" (3.2 mm)
<b>Selvage Edge</b>	3/32" (2.4 mm) ± 1/32" (0.8 mm)	
<b>Weight<sup>(c)</sup></b>	ozs/in <sup>2</sup> (g/cm <sup>2</sup> )	
	0.021 (0.090)	0.021 (0.090)
<b>Liner</b>	White 3 mil polypropylene film with red "3M™ Scotchmate™" printing	

a) Other colors are available as special orders. Some discoloration of the white product may be a natural occurrence. The adhesive may produce a yellow tint to some light colored hook and loop products. Therefore, 3M recommend the user to evaluate the products to see if it meets their color requirements. See your 3M authorized distributor or 3M representative for color selection guide and minimum requirements.

b) Thickness depends upon the amount of compression load on the pieces.

c) All thickness and weight values are with the liner removed.

# 3M™ Scotchmate™ Reclosable Fasteners

SJ3586FR and SJ3587FR

Polyester Flame Resistant Hook and Loop

## Typical System Performance Characteristics

**Note:** The following technical information is not product release requirements, but rather represent typical performance using standard test methods and is intended for use as a guide to assist in selection of 3M™ Scotchmate™ Reclosable Fasteners for further evaluation. This technical information should not be used for setting standards.

Unless stated differently, typical system performance characteristics were measured under controlled laboratory conditions of 72°F (22°C) and 50% Relative Humidity to obtain maximum reliability. The user should evaluate products in the actual application to ensure suitable performance for the intended use.

<b>System Performance<sup>(a)</sup></b>	
<b>3M™ Scotchmate™ Reclosable Fastener SJ3587FR loop engaged to 3M™ Scotchmate™ Reclosable Fastener SJ3586FR hook</b>	
<b>TENSILE (Rigid to Rigid Substrates)</b>	Pounds <sub>F</sub> /sq inch (kNewtons/m <sup>2</sup> ):
Dynamic Tensile Engagement Strength	< 1.0 (< 6.9)
Dynamic Tensile Disengagement <sup>(b)</sup>	9.0 (62)
Static Tensile Holding Power	Holds 1.1#/in <sup>2</sup> (77.5 grams/cm <sup>2</sup> ) for indicated time in minutes at the indicated temperature
120°F	400
140°F	400
158°F	300
100°F/100% RH	60
<b>SHEAR (Rigid to Rigid Substrates)</b>	Pounds <sub>F</sub> /sq inch (kNewtons/m <sup>2</sup> ):
Dynamic Shear (1" x 1" overlap) <sup>(b)</sup>	17.3 (119)
Static Shear Holding Power	Holds 1.1#/in <sup>2</sup> (77.5 grams/cm <sup>2</sup> ) for indicated time in minutes at the indicated temperature
120°F	2,000
140°F	2,000
158°F	500
100°F/100% RH	60
<b>PEEL AND CLEAVAGE<sup>(b)</sup></b>	Pounds <sub>F</sub> /inch width (grams <sub>F</sub> /cm width)
Peak Cleavage Strength (Rigid to Rigid)	7.2 (1300)
Peak Peel Strength ("T" Peel, Flexible to Flexible)	2.6 (460)
Peak Peel Strength (90° Peel, Flexible to Rigid)	2.4 (430)
<b>ENGAGED THICKNESS<sup>(c)</sup></b> (Nominal without liner)	Inches (mm) ± Tolerance 0.18 (4.5) ± 20%
<b>CLOSURE CYCLE LIFE<sup>(d)</sup></b>	1,000
<b>SHELF LIFE<sup>(e)</sup></b>	18 months

**Note: Long Term Static Load:** Conditions such as temperature variations, engagement area, closure pressure and vibrations or side-to-side movement after engagement or exposure to prolonged periods of moisture or other environmental factors can affect the closure strength and long term static load performance. Fasteners may slip or creep in the direction of the static load forces at temperatures or weights greater than indicated. The user is responsible for designing the amount of fastening area based upon the specific conditions for the application. Four square inches of fastening area per pound of static load is suggested as a starting point for such evaluations.

- a) System performance tests are determined by measuring the performance of the entire mated reclosable fastener system (two - 1/16 in. thick non-anodized aluminum plates joined together with the indicated fasteners).
- b) 3M™ Scotchmate™ Reclosable Fasteners SJ3586FR and SJ3587FR are engaged with firm pressure and disengaged, peeled or cleaved at the rate of 12 inches (305 mm) per minute. The "T" peel, only has the closure performance measured per ASTM D5170 and was not adhered to aluminum panels. The 90° peel has one of the mated fasteners attached to a non-anodized aluminum plate while the other mated fastener is disengaged at a 90° angle.
- c) Engaged thickness is measured with a 1/2 in. diameter pressure foot with a 34 gram weight and will decrease if a load is applied or increase if a separation (tensile) force is applied.
- d) Cycle Life is the number of cycles (openings and closings) the fastener can provide while maintaining 50% or greater of the original peel values.
- e) Shelf life is from date of manufacture when stored in original packaging between 60° to 80°F (16° to 27°C) and 40 to 60% relative humidity.

# 3M™ Scotchmate™ Reclosable Fasteners

SJ3586FR and SJ3587FR

Polyester Flame Resistant Hook and Loop

## Typical Physical Properties and Characteristics

**Note:** The following technical information is not product release requirements, but rather represent typical performance using standard test methods and is intended for use as a guide to assist in selection of 3M™ Scotchmate™ Reclosable Fasteners for further evaluation. This technical information should not be used for setting standards.

Unless stated differently, typical physical properties and characteristics were measured with the fastener not attached to a substrate, under controlled laboratory conditions of 72°F (22°C) and 50% Relative Humidity to obtain maximum reliability. The user should evaluate products in the actual application to ensure suitable performance for the intended use.

Flammability Tests		3M™ Scotchmate™ Reclosable Fastener SJ3587FR (loop)	3M™ Scotchmate™ Reclosable Fastener SJ3586FR (hook)
<b>FAR 25.853 Para. (a)(1)(ii) 12 Second Vertical</b>			
<b>Test</b>	<b>Spec. (max., average) of three</b>		
Burn Length (inches)	8	2	2.6
Extinguish Time <sup>(a)</sup> (seconds)	15	2.6	1.2
Drip Ext. Time (seconds)	3	1	1
<b>FAR 25.853 Para. (a)(1)(iv) 15 Second Horizontal (2.5"/minute)</b>			
<b>Test</b>	<b>Spec. (max.)</b>		
Average Burn Rate <sup>(b)</sup>	2.5"/minute	EBRTZ	EBRTZ
<b>FAR 25.853 Para. (a)(1)(v) 15 Second Horizontal (4.0"/minute)</b>			
<b>Test</b>	<b>Spec. (max.)</b>		
Average Burn Rate	4"/minute	EBRTZ	EBRTZ

a) Extinguish time refers to the time it takes the burning matter to extinguish after the flame source is removed.

b) EBRTZ means the product extinguished before the flame reached the time zone.

## Additional Performance Characteristics

**Solvent Resistance:** The polyester components of the hook and loop resist incidental attack by most common solvents and alkaline solutions. Acid solutions may cause deterioration of the fastener. The adhesive on 3M™ Scotchmate™ Reclosable Fasteners SJ3586FR and SJ3587FR may be affected by many common organic laboratory solvents and transportation fluids (gasoline, motor oil, etc.).

**Plasticizer Resistance:** The adhesive on Scotchmate reclosable fasteners SJ3586FR and SJ3587FR may be affected by plasticizers found in many common flexible vinyl or other material that may result in softening or adhesion loss over time. These products are not recommended for adhering to plasticized materials.

**Flammability Resistance:** Scotchmate reclosable fasteners SJ3586FR and SJ3587FR have not been tested to other standard flammability tests such as FMVSS-302, ASTM E-162, ASTM E-662, BSS-7239, UL94.

**Environmental Effects:** Temperatures down to -20°F (-29°C) increases the typical closure strengths. This polyester product will have good outdoor weathering resistance when exposed to ultraviolet light and moisture.

**Water (Humidity) Resistance:** Closure strength of polyester hook and loop fasteners maintains its strength better than nylon products after prolonged exposure to water caused by water absorption of the cut ends for the hook products. Closure strength is regained when dried. Once bonded the adhesive has high resistance to moisture under typical use conditions.

# 3M™ Scotchmate™ Reclosable Fasteners

SJ3586FR and SJ3587FR

Polyester Flame Resistant Hook and Loop

**Additional Performance Characteristics**  
(continued)

**Volatile Outgassing:** Volatile outgassing, as per ASTM E595, is one important test in determining the suitability of materials for spacecraft. Generally products with acrylic or no adhesive have lower volatile outgassing values. 3M™ Scotchmate™ Reclosable Fasteners SJ3586FR and SJ3587FR would not be expected to pass ASTM E595. Products tested at the Goddard Space Flight Center can be found at the following web site: <http://outgassing.nasa.gov/>. If flame resistance is not critical, then our nylon 3M™ Scotchmate™ Reclosable Fasteners SJ3571, SJ3572 and SJ3595 or our polyester 3M™ Scotchmate™ Reclosable Fasteners SJ3576 or SJ3577 could be evaluated for low outgassing.

**Sterilization/Autoclaving:** Scotchmate reclosable fasteners SJ3586FR and SJ3587FR have not been exposed to gas or steam sterilization, or autoclaving. Plain back products such as nylon 3M™ Scotchmate™ Reclosable Fasteners SJ3418FR, SJ3419FR or polyester 3M™ Scotchmate™ Reclosable Fasteners SJ3486FR or SJ3487FR have not been exposed to sterilization or autoclaving, but would be expected to perform better than adhesively coated products.

**Washing and Dry Cleaning:** Scotchmate reclosable fasteners SJ3586FR and SJ3587FR, attached to fabrics will typically shrink less than 5% unless the fabric has greater shrinkage amounts. Washing or dry cleaning of these products is not recommended due to adhesive softening that could transfer adhesive residues to other materials.

**Fungus Resistance:** Scotchmate reclosable fasteners SJ3586FR and SJ3587FR have not been tested for fungus resistance and should be evaluated by the customer under conditions applicable to the expected end use.

**Static Discharge:** Scotchmate reclosable fasteners SJ3586FR and SJ3587FR have not been tested for discharge during liner removal, closure opening, or adhesive removal from the substrate once a fastener has been applied. If your application requires use of these fasteners in areas where static discharge is of a concern, the fasteners should be tested under expected use conditions.

**Available Sizes<sup>(a)</sup>**

**3M™ Scotchmate™ Reclosable Fasteners  
SJ3586FR (Hook) and SJ3587FR (Loop)**

Width <sup>(a)</sup> inch ± 1/16 (mm) ± 1.6	Roll Length Yards (Meters)	Roll Weight (with side shields and grommets)	Selvedge Edge <sup>(b)</sup>	Extended Liner <sup>(b)</sup>
		Pounds (Kilograms)		
5/8" (15.9 mm)	50 yds. (45.7 meters)	1.9 (0.85)	One Edge	One Edge
3/4" (19 mm)	50 yds. (45.7 meters)	2.1 (0.95)	One Edge	One Edge
1" (25.4 mm)	50 yds. (45.7 meters)	2.8 (1.3)	One Edge	One Edge
1-1/2" (38.1 mm)	50 yds. (45.7 meters)	4.1 (1.9)	Two Edges	Two Edges
2" (50.8 mm)	50 yds. (45.7 meters)	5.3 (2.4)	Two Edges	Two Edges

**Fabricated Forms<sup>(c)</sup>**

**Cut Pieces**

a) Scotchmate reclosable fasteners SJ3586FR or SJ3587FR products are available on standard 3" diameter cores. Scotchmate reclosable fasteners SJ3586FR and SJ3587FR are available up to 4" wide as a special order. An additional 1/4" should be added to the product width to account for the side shields supplied with the product. The diameter of the side shield is 17.5 inches. Contact your 3M authorized distributor or 3M representative for details on supplying special sizes.

b) Other configurations may be possible as a special order.

c) 3M™ Scotchmate™ Reclosable Fasteners can be fabricated in many custom shapes and sizes to fit your product design and manufacturing process. Contact your local 3M authorized converter or 3M representative for additional options, configurations and ordering information.

# 3M™ Scotchmate™ Reclosable Fasteners

SJ3586FR and SJ3587FR

Polyester Flame Resistant Hook and Loop

---

## Attachment Techniques

The following information is intended to assist the designer considering the use of adhesively coated 3M™ Scotchmate™ Reclosable Fasteners. Product performance depends upon a number of factors, including the fastener selected, the conditions in which the fastener is applied and the time and environmental conditions in which it is expected to perform. Because many of these factors are uniquely within the user's knowledge and control, it is required that the user evaluate 3M products to determine whether it is fit for a particular purpose and suitable for the user's substrates, method of application and desired end use.

**Design Considerations:** As a general rule, four square inches of fastener area per pound of static load to be supported is suggested as a starting point for evaluation. More or less area may be needed depending on specific conditions or end use applications.

Rounding the corners, recessing the product into the substrate and providing raised edges around the reclosable fastener can reduce the possibility of edge lifting, and improve the overall appearance on the fastener on the finished product. Mechanically securing the corners of the reclosable fastener can also reduce the possibility of edge lifting, but may reduce the closure performance.

**Attachment Methods:** The three most important techniques for attaching 3M™ Scotchmate™ Reclosable Fasteners SJ3586FR and SJ3587FR to various surfaces are summarized below. For complete details on techniques and options for attaching Scotchmate Reclosable Fasteners please see the technical bulletin "Attachment of 3M™ Scotchmate™ and Dual Lock™ Reclosable Fasteners" (70-0709-3929-6).

**1) Pressure Sensitive Adhesive attachment:** The use of pressure sensitive adhesives eliminates or reduces the need for sewing, solvent activation, dielectric or ultrasonic bonding and bulk adhesive bonding. This can result in simplicity, greater safety and lower installation costs. Pressure sensitive products can be applied manually or automatically using a variety of equipment choices. Contact your 3M Sales Representative to discuss automated equipment options.

**Substrate Surface Preparation:** Adhesive backed 3M™ Reclosable Fasteners such as 3M™ Scotchmate™ products should be applied to surfaces that are clean, dry, and free of oil, grease, dust, mold release agents or other contaminants that could reduce the adhesion. Highly textured substrate surfaces or surface contaminants may reduce the ultimate adhesion levels. It is recommended to remove any surface contaminants or minimize surface texture or roughness that may reduce adhesion by using a method suited for the type and quantity of surface contaminants present.

In exceptional cases, especially when removing silicone mold release agents or on rough or porous surfaces, it may be necessary to sand or abrade the surface, use an adhesive primer, or surface sealer to optimize bond performance. The selection of priming or sealing materials will depend on the substrates and the environmental conditions the product will be exposed to during use, as well as regulations concerning use of certain materials or chemicals.

**Note:** When using cleaning agents such as solvents or abrasives, it is important to follow all manufacturer's precautions and directions for use as well as government regulations or customer requirements.

# 3M™ Scotchmate™ Reclosable Fasteners

SJ3586FR and SJ3587FR

Polyester Flame Resistant Hook and Loop

---

## Attachment Techniques (continued)

**Attachment Procedure:** To obtain an optimum bond to any surface, both the fasteners and the target surface should have equilibrated at temperatures between 70°F (21°C) and 100°F (38°C) for a minimum of 1 hour before application. Remove the adhesive liner from the fasteners adhesive and without touching the adhesive apply the adhesive side of the fastener to the pre-cleaned and prepared surface. Using finger pressure, press the fastener onto the substrate to obtain initial surface contact between the adhesive and substrate. If the substrate is flexible, make sure it is laying on a hard flat surface so as to permit uniform application of the adhesive. Use of a rubber hand roller, press platen or similar device is recommended to ensure full contact of adhesive with the substrate. Three passes in each direction, with special attention paid to rolling down the edges, should be adequate.

**Dwell Time before Handling or Applying a Load:** Parts with properly chosen and applied reclosable fasteners with pressure sensitive adhesives can be handled immediately. Adhesive bond strength increases after application with time, pressure and/or temperature, as the adhesive further wets out the substrate surface. This dwell time is important for achieving a firm adhesive bond before applying a load or using. Once attached to the substrate, a 1-hour minimum dwell time is recommended before applying a load or disengaging. This adhesive achieves approximately 50% of the ultimate bond strength within 20 minutes, 90% after 1 hour and the ultimate bond strength is obtained within 24 hours at 72°F (22°C) and 50% relative humidity. The use of primers or adhesion promoters may reduce the time required to achieve the ultimate bond strength.

**2) Heat (Press) Bonding:** 3M™ Scotchmate™ Reclosable Fasteners SJ3586FR (hook) and SJ3587FR (loop) can be attached to many fabric and foam articles by press bonding. The fastener is initially adhered to the article using finger pressure. Bond strength is increased by applying heat and pressure through the substrate to the adhesive side of the fastener for given pressure, times and heating period. For properly chosen press bonding conditions the product can be used immediately after cooling, usually a matter of seconds. Once applied these fasteners should not be washed or dry cleaned. Product performance will depend upon the nature of the fabric or foam and other conditions within any specific application. For this reason it is essential that the user evaluate the product to determine if it is fit for a particular purpose and suitable for the user's method of application.

**Typical Press Bonding Conditions:**

Bonding Temperature: 250 to 425°F (121 to 218°C)

Bonding Pressure: 30 to 100 psi (207 to 690 kPa)

Bonding Time: 3 to 30 seconds.

**3) Mechanical Attachment:** Scotchmate reclosable fasteners SJ3586FR and SJ3587FR may also be mechanically attached to difficult to adhere to surfaces such as textured plastics and wood by using staples, screws or rivets. The head of the mechanical fastener should be flat and large enough to resist pull through when the fastener is disengaged. The head of the fastener should also be recessed as much as possible below the surface of the hook or loop to prevent interference with (dis)engagement properties.

The use of resin coated chisel divergent staples appear to provide excellent attachment to thick sections of soft and hardwood surfaces.

# 3M™ Scotchmate™ Reclosable Fasteners

SJ3586FR and SJ3587FR

Polyester Flame Resistant Hook and Loop

---

## Application Ideas

3M™ Scotchmate™ Reclosable Fasteners SJ3586FR and SJ3587FR can provide a firm adhesive bond to a wide variety of surfaces, including, but not limited to those listed below. Because product performance will depend on actual conditions within any specific application, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular material purpose and suitable for the user's method of application.

### Plastics

Paper	Cardboard	Acrylic	Polypropylene
Glass	Sealed Wood	Polycarbonate	Polystyrene
Fabrics	Bare and Painted Metal	Polyethylene	Rigid Vinyl

Not recommended for attaching to flexible vinyl or plasticized plastics.

Scotchmate reclosable fasteners SJ3586FR and SJ3587FR has shown to be useful for:

Anti-scratch surface	Vibration and sound dampening control
Panels in Rail Vehicles	Airline Interiors and Seating
Insulation Blanket Closures	Electronic Cover Plates

# 3M™ Scotchmate™ Reclosable Fasteners

SJ3586FR and SJ3587FR

Polyester Flame Resistant Hook and Loop

---

## Certification/ Recognition

**MSDS:** 3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.

**TSCA:** These products are defined as an article under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.

**Military Spec. MIL-F-21840G:** 3M™ Scotchmate™ Reclosable Fasteners SJ3586FR and SJ3587FR meet the physical requirements of Mil spec. MIL-F-21840G, Type III Class 3. Note that Class 5 requirements are met by mating Scotchmate reclosable fastener SJ3587FR to 3M™ Scotchmate™ Reclosable Fastener SJ3519FR.

**C.I.D. A-A-55126A:** Mil Spec. A-A-55126A supersedes mil spec. MIL-F-21840G. Scotchmate reclosable fasteners SJ3586FR and SJ3587FR have not been tested to the requirements of this CID as it has lower performance and contains errors and omissions.

---

## Product Use

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

---

## Warranty and Limited Remedy

Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

---

## Limitation of Liability

Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**ISO 9001:2000 - ISO/TS 16949:2002**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 and ISO/TS 16949:2002 standards.

# 3M

**Industrial Business  
Industrial Adhesives and Tapes Division**

3M Center, Building 21-1W-10, 900 Bush Avenue  
St. Paul, MN 55144-1000  
800-362-3550 • 877-369-2923 (fax)  
www.3M.com/industrial



*Recycled Paper  
40% pre-consumer  
10% post-consumer*

Printed in U.S.A.  
©3M 2005 70-0709-3978-3 (3/05)