

March, 2016

3M™ Double Coated Acrylic Tape 9088-200

Product Description

3M™ Double Coated Tapes with 3M™ Modified Acrylic Adhesive 375 provides an excellent balance of adhesive peel and shear performance. The adhesive system used on this product provides good adhesion to both high and low surface energy substrates. The initial tack provided ensures that a bond of good integrity is achieved soon after application.



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Notes
Total Tape Thickness without liner	0.2 mm	7.9 mil	
Adhesive 1 (Faceside) Thickness	0.094 mm	3.7 mil	Adhesive 1 is on the interior of the roll, exposed when unwound, Adhesive 2 is on the exterior of the roll, exposed when liner is removed. The thickness listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc. While past data pages have listed nominal thicknesses, the coat weight (and theoretical caliper) has not changed.
Adhesive 2 (Backside) Thickness	0.094 mm	3.7 mil	Adhesive 1 is on the interior of the roll, exposed when unwound, Adhesive 2 is on the exterior of the roll, exposed when liner is removed. The thickness listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc. While past data pages have listed nominal thicknesses, the coat weight (and theoretical caliper) has not changed.
Carrier Thickness	0.012 mm	0.5 mil	
Faceside Adhesive Type	Acrylic		Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.
Backside Adhesive Type	Acrylic		Backside adhesive is on the exterior of the roll, exposed when liner is removed.
Adhesive Carrier	PET (Polyester)		

Table continued on next page

Typical Physical Properties (continued)

Property	Values		Notes
Liner	58# Glassine		
Liner Thickness	0.08 mm	3.2 mil	

Typical Performance Characteristics

90° Peel Adhesion		Substrate
17.4 N/cm	159 oz/in	Stainless Steel
14.8 N/cm	135 oz/in	ABS
16.7 N/cm	153 oz/in	Glass
18.2 N/cm	166 oz/in	Polycarbonate (PC)
6 N/cm	55 oz/in	High Density Polyethylene (HDPE)

Property: 90° Peel Adhesion
Method: ASTM D3330
Dwell/Cure Time: 72 hr @ Room Temperature
Backing: Aluminum Foil

Property	Values	Test Condition	Notes
Static Shear	10000 min	1000 g load @ Room Temperature	1in x 1in size; test terminated after 10,000 minutes
Static Shear	10000 min	500 g load @ 70°C (158°F)	1in x 1in size; test terminated after 10,000 minutes

Available Sizes

Master Width			
1220 mm	55 yd	50 m	48 in

Property: Master Width
notes: More sizes may be available. Please call 800-223-7427 or talk to your local 3M representative for more information.

Environmental Performance

UV Resistance – When properly applied, nameplates and decorative trim parts are not adversely affected by outdoor exposure.

Bond Build-up: The bond strength of 3M™ Adhesive 375 increases as a function of time and temperature.

Temperature/Heat Resistance: Adhesive 375 is usable for short periods (minutes, hours) at temperatures up to 300°F (150°C) and for intermittent longer periods (days, weeks) up to 195°F (90°C).

Lower Temperature Service Limit: -10°F (-23°C).

Handling/Application Information**Application Ideas**

- Point of Purchase Displays
- Indoor/Outdoor Signage
- Paper Bonding and Packaging
- Splicing
- Mounting of Plastic Parts
- Mounting of Furniture and Decorative Trims

3M™ Double Coated Acrylic Tape 9088-200

Storage and Shelf Life

It is suggested that products are stored at room temperature conditions of 70°F (21°C) and 50% relative humidity. If stored properly, product retains its performance and properties for 24 months from date of manufacture.

Trademarks

3M is a trademark of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~ /3M-High-Performance-Double-Coated-Tape-9088-200?N=5002385+3292678975&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=9088-200

Family Group

	9086	9087	9088 to 200	9088F200
Total Tape Thickness without liner (mm)	0.019	0.26	0.2	0.2
Adhesive 1 (Faceside) Thickness (mm)			0.094	0.094
Adhesive 2 (Backside) Thickness (mm)			0.094	0.094
Carrier Thickness (mm)		0.038	0.012	0.012
Faceside Adhesive Type			Acrylic	Acrylic
Backside Adhesive Type			Acrylic	Acrylic
Adhesive Carrier	Tissue	PVC	PET (Polyester)	PET (Polyester)
Liner	Paper (Glassine)	Paper (Glassine)	58# Glassine	Polypropylene Film
Liner Thickness (mm)	0.07	0.07	0.08	0.08

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Bottom Matter Images

[Image 4]

[Image 5]

Recognition/Certification

TSCA: This product is defined as an article under the Toxic Substances Control Act and therefore, it is exempt from inventory listing requirements

SDS: 3M has not prepared a SDS for this product which is not subjected to the SDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R.1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, this product should not present a health and safety hazard. However, use or processing of the product in a manner not in accordance with the directions for use may affect its performance and present potential health and safety hazards.

Note: One of 3M's core values is to respect our social and physical environment. 3M is committed to comply with ever-changing, global, regulatory and consumer environmental, health, and safety (EHS) requirements. As a service to our customers, 3M is providing information on the regulatory status of many 3M products. Further regulation information including that for OSHA, USCPSI, FDA, California Proposition 65, READY and RoHS, can be found at 3M.com/regs.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

